

Please type a plus sign (+) inside this box → ☐

PTO/SB/05 (11-00)

Approved for use through 10/31/2002. OMB 0651-0032

U.S. Patent and Trademark Office. U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number

**UTILITY  
PATENT APPLICATION  
TRANSMITTAL**

(Only for new nonprovisional applications under 37 C.F.R. 1.53(b))

Attorney Docket No.	5000 89A
First Inventor	Hua-Shuang Kong et al.
Title	Susceptor Designs for Silicon Carbide Thin Films
Express Mail Label No.	EL473031092US

**APPLICATION ELEMENTS**

See MPEP chapter 600 concerning utility patent application contents.

- 1 ☒ Fee Transmittal Form (e.g., PTO/SB/17)  
(Submit an original and a duplicate for fee processing)
- 2 ☐ Applicant claims small entity status.  
See 37 CFR 1.27.
- 3 ☒ Specification [Total Pages 23]  
(preferred arrangement set forth below)  
- Descriptive title of the invention  
- Cross References to Related Applications  
- Statement Regarding Fed sponsored R & D  
- Reference to sequence listing, a table,  
or a computer program listing appendix  
- Background of the invention  
- Brief Summary of the invention  
- Brief Description of the Drawings (if filed)  
- Detailed Description  
- Claim(s)  
- Abstract of the Disclosure
- 4 ☒ Drawing(s) (35 U.S.C. 113) [Total Sheets 6]  
5. Oath or Declaration [Total Pages 3]  
a. ☐ Newly executed (original or copy)  
b. ☒ Copy from a prior application (37 CFR 1.63 (d))  
(for a continuation/divisional with Box 18 completed)  
i ☐ **DELETION OF INVENTOR(S)**  
Signed statement attached deleting inventor(s)  
named in the prior application, see 37 CFR  
1.63(d)(2) and 1.33(b)
- 6 ☐ Application Data Sheet. See 37 CFR 1.76

**ADDRESS TO:**Assistant Commissioner for Patents  
Box Patent Application  
Washington, DC 20231

- 7 ☐ CD-ROM or CD-R in duplicate, large table or  
Computer Program (Appendix)
8. Nucleotide and/or Amino Acid Sequence Submission  
(if applicable, all necessary)  
a. ☐ Computer Readable Form (CRF)  
b. Specification Sequence Listing on:  
i. ☐ CD-ROM or CD-R (2 copies); or  
ii. ☐ paper  
c. ☐ Statements verifying identity of above copies

**ACCOMPANYING APPLICATIONS PARTS**

- 9 ☐ Assignment Papers (cover sheet & document(s))
- 10 ☐ 37 C.F.R. §3.73(b) Statement ☐ Power of  
(when there is an assignee) Attorney
- 11 ☐ English Translation Document (if applicable)
- 12 ☒ Information Disclosure ☐ Copies of IDS  
Statement (IDS)/PTO-1449 Citations
- 13 ☒ Preliminary Amendment
- 14 ☒ Return Receipt Postcard (MPEP 503)  
(Should be specifically itemized)
- 15 ☐ Certified Copy of Priority Document(s)  
(if foreign priority is claimed)
- 16 ☐ Request and Certification under 35 U.S.C. 122  
(b)(2)(B)(i). Applicant must attach form PTO/SB/35  
or its equivalent.
- 17 ☐ Other:

18. If a CONTINUING APPLICATION, check appropriate box, and supply the requisite information below and in a preliminary amendment,  
or in an Application Data Sheet under 37 CFR 1.76:

☒ Continuation ☐ Divisional ☐ Continuation-in-part (CIP)  
Prior application information: Examiner E. Fieler


of prior application No. 08 / 823 365  
Group / Art Unit: 1763

For CONTINUATION or DIVISIONAL APPS only: The entire disclosure of the prior application, from which an oath or declaration is supplied  
under Box 5b, is considered a part of the disclosure of the accompanying or divisional application and is hereby incorporated by reference.  
The incorporation can only be relied upon when a portion has been inadvertently omitted from the submitted application parts.

**17. CORRESPONDENCE ADDRESS**

☒ Customer Number or Bar Code Label 021176 or ☐ Correspondence address below  
(Insert Customer No. or Attach bar code label here)

Name	Stanley B. Baker				
	Philip Summa, P.A.				
Address	13777 Ballantyne Corporate Place				
	Suite 315				
City	Charlotte	State	NC	Zip Code	28277
Country		Telephone	704-945-6701	Fax	704-945-6735

Name (Print/Type)	Stanley B. Baker	Registration No. (Attorney/Agent)	35,058
Signature		Date	November 17, 2000

Burden Hour Statement: This form is estimated to take 0.2 hours to complete. Time will vary depending upon the needs of the individual case. Any  
comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, U.S. Patent and Trademark  
Office, Washington, DC 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO Assistant Commissioner for  
Patents, Box Patent Application, Washington, DC 20231.

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number

# FEE TRANSMITTAL for FY 2001

Patent fees are subject to annual revision

Complete if Known

Application Number

Filing Date

First Named Inventor

Examiner Name

Group / Art Unit

Attorney Docket No.

Concurrently Herewith

Hua-Shuang Kong et al.

5000.89A

TOTAL AMOUNT OF PAYMENT (\$ 836

## METHOD OF PAYMENT (check one)

1. ☒ The Commissioner is hereby authorized to charge indicated fees and credit any over payments to:

Deposit  
Account  
Number

50-0332

Deposit  
Account  
Name

Philip Summa, P.A.

- ☒ Charge Any Additional Fee Required  
Under 37 CFR 1.16 and 1.17  
☐ Applicant claims small entity status.  
See 37 CFR 1.27

2. ☒ Payment Enclosed:

☒ Check ☐ Credit card ☐ Money  
Order ☐ Other

## FEE CALCULATION

### 1. BASIC FILING FEE

Large Fee Code	Entity Fee (\$)	Small Fee Code	Entity Fee (\$)	Fee Description	Fee Paid
101	710	201	355	Utility filing fee	710
106	320	206	160	Design filing fee	
107	490	207	245	Plant filing fee	
108	710	208	355	Reissue filing fee	
114	150	214	75	Provisional filing fee	

SUBTOTAL (1)

(\$ 710

### 2. EXTRA CLAIM FEES

	Total Claims	Extra Claims	Fee from below	Fee Paid
	27	-20** = 7	X 18 =	126
Independent Claims	3	-3** = 0	X 40 =	0
Multiple Dependent			X =	0

Large Fee Code	Entity Fee (\$)	Small Fee Code	Entity Fee (\$)	Fee Description
103	18	203	9	Claims in excess of 20
102	80	202	40	Independent claims in excess of 3
104	270	204	135	Multiple dependent claim, if not paid
109	80	209	40	** Reissue independent claims over original patent
110	18	210	9	** Reissue claims in excess of 20 and over original patent

SUBTOTAL (2) (\$ 126

\*\*or number previously paid, if greater; For Reissues, see above

## FEE CALCULATION (continued)

### 3. ADDITIONAL FEES

Fee Code	Large Entity Fee (\$)	Fee Code	Small Entity Fee (\$)	Fee Description	Fee Paid
105	130	205	65	Surcharge - late filing fee or oath	
127	50	227	25	Surcharge - late provisional filing fee or cover sheet	
139	130	139	130	Non-English specification	
147	2,520	147	2,520	For filing a request for reexamination	
112	920*	112	920*	Requesting publication of SIR prior to Examiner action	
113	1,840*	113	1,840*	Requesting publication of SIR after Examiner action	
115	110	215	55	Extension for reply within first month	
116	390	216	195	Extension for reply within second month	
117	890	217	445	Extension for reply within third month	
118	1,390	218	695	Extension for reply within fourth month	
128	1,890	228	945	Extension for reply within fifth month	
119	310	219	155	Notice of Appeal	
120	310	220	155	Filing a brief in support of an appeal	
121	270	221	135	Request for oral hearing	
138	1,510	138	1,510	Petition to institute a public use proceeding	
140	110	240	55	Petition to revive - unavoidable	
141	1,240	241	620	Petition to revive - unintentional	
142	1,240	242	620	Utility issue fee (or reissue)	
143	440	243	220	Design issue fee	
144	600	244	300	Plant issue fee	
122	130	122	130	Petitions to the Commissioner	
123	130	123	130	Petitions related to provisional applications	
126	180	126	180	Submission of Information Disclosure Stmt	
581	40	581	40	Recording each patent assignment per property (times number of properties)	
146	710	246	355	Filing a submission after final rejection (37 CFR § 1.129(a))	
149	710	249	355	For each additional invention to be examined (37 CFR § 1.129(b))	
179	710	279	355	Request for Continued Examination (RCE)	
169	900	169	900	Request for expedited examination of a design application	

Other fee (specify)


\*Reduced by Basic Filing Fee Paid

SUBTOTAL (3)

(\$ 0

## SUBMITTED BY

Complete (if applicable)

Name (Print/Type)	Stanley B Baker	Registration No. Attorney/Agent)	35,058	Telephone	704-945-6707
Signature				Date	November 17, 2000

WARNING: Information on this form may become public. Credit card information should not be included on this form. Provide credit card information and authorization on PTO-2038.

Burden Hour Statement: This form is estimated to take 0.2 hours to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, U.S. Patent and Trademark Office, Washington, DC 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Assistant Commissioner for Patents, Washington, DC 20231.

Attorney Docket No. 5000.89A

**PATENT**

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re: Hua-Shuang Kong et al.

Serial No.:

Filed: Concurrently Herewith

For: SUSCEPTOR DESIGNS FOR SILICON CARBIDE  
THIN FILMS

November 17, 2000

Assistant Commissioner for Patents  
Washington, DC 20231

**PRELIMINARY AMENDMENT**

Sir:

After the title, please insert

-- Cross-Reference to Related Application

This application is a divisional of copending U.S. application Serial No. 08/823,365, filed March 24, 1997. --.

In the Claims:

Please cancel Claims 8, 9, 11-20, and 33-41, without prejudice before calculating the filing fee.

Respectfully submitted,



Stanley B. Baker  
Reg. No. 35,058

021176

**Philip Summa, P.A.**

13777 Ballantyne Corporate Place  
Suite 315

Charlotte, North Carolina 28277


Telephone: 704-945-6700

Facsimile: 704-945-6735

S:\FIRM DOCS\5000\89A\Pre. Amendment.doc

Express Mail Label Number EL473031092US  
Date of Deposit: November 17, 2000

I hereby certify that this paper or fee is being deposited with the United States Postal Service "Express Mail Post Office to Addressee" service under 37 CFR 1.10 on the date indicated above and is addressed to Assistant Commissioner for Patents, Box: Patent Application, Washington, DC 20231.

  
Andie Crumpler

# SUSCEPTOR DESIGNS FOR SILICON CARBIDE THIN FILMS

## Field of the Invention

The present invention relates to semiconductor manufacturing processes, and in particular relates to an improved susceptor design for epitaxial growth on silicon carbide substrates.

## Background of the Invention

The present invention relates to the production of epitaxial layers of semiconductor materials on silicon carbide substrates. Silicon carbide offers a number of advantageous physical and electronic characteristics for semiconductor performance and devices. These include a wide bandgap, high thermal conductivity, high saturated electron drift velocity, high electron mobility, superior mechanical strength, and radiation hardness.

As is the case with other semiconductor materials such as silicon, one of the basic steps in the manufacture of a number of silicon-carbide based devices includes the growth of thin single crystal layers of semiconductor material on silicon carbide substrates. The technique is referred to as "epitaxy," a term that describes crystal growth by chemical reaction used to form, on the surface of another crystal, thin layers of semiconductor materials with defined lattice structures. In many cases, the lattice structure of the epitaxial layers (or "epilayers") are either identical, similar, or otherwise related to the lattice structure of the substrate. Thus, epitaxial growth of either silicon carbide epitaxial layers on silicon carbide substrates or of other semiconductor materials on silicon carbide substrates, is a fundamental technique for manufacturing devices based on silicon carbide.

Silicon carbide is, however, a difficult material to work with because it can crystallize in over 150 polytypes, some of which are separated from one another by very small thermodynamic differences. Furthermore, because of silicon carbide's high melting point (over 2700°C), many processes for working silicon carbide, including epitaxial film deposition, often need to be carried out at much higher temperature than analogous reactions in other semiconductor materials.

Some basic reviews of semiconductor manufacturing technology can be found for example in Sze, Physics of Semiconductor Devices, 2d Ed. (1981), Section 2.2, pages 64-73; or in Dorf, The Electrical Engineering Handbook, CRC Press, (1993) at Chapter 21 "Semiconductor Manufacturing," pages 475-489; and particularly in Sherman, Chemical Vapor Deposition for Microelectronics: Principles, Technologies and Applications, (1987), ISBN 0-8155-1136-1. The techniques and apparatus discussed herein can be categorized as chemical vapor deposition (CVD) or vapor phase epitaxy (VPE) in which reactant gases are exposed to an energy source (e.g. heat, plasma, light) to stimulate a chemical reaction, the product of which grows on the substrate.

There are several basic techniques for CVD epitaxial growth, the two most common of which are the hot (heated) wall reactor and cold wall reactor processes. A hot wall system is somewhat analogous to a conventional oven in that the substrate, the epitaxial growth precursor materials, and the surrounding container are all raised to the reaction temperature. The technique offers certain advantages and disadvantages.

The second common conventional technique is the use of a "cold wall" reactor. In such systems, the substrate to be used for epitaxial growth is placed on a platform within a container (typically formed of quartz or stainless steel). In many systems, the substrate is disk-shaped and referred to as

a "wafer." The substrate platform is made of a material that will absorb, and thermally respond to, electromagnetic radiations.

As is known to those familiar with such devices and techniques, the susceptor's response to electromagnetic radiation is an inductive process in which alternating frequency electromagnetic radiation applied to the susceptor generates an induced (inductive) current in the susceptor. The susceptor converts some of the energy from this inductive current into heat. In many systems, the electromagnetic radiation is selected in the radio frequency (RF) range because materials such as glass and quartz are transparent to such frequencies and are unaffected by them. Thus, the electromagnetic radiation passes through the container and is absorbed by the susceptor which responds by becoming heated, along with the wafer, to the temperatures required to carry out the epitaxial growth. Because the container walls are unaffected by the electromagnetic energy, they remain "cold" (at least in comparison to the susceptor and the substrate), thus encouraging the chemical reaction to take place on the substrate.

A thorough discussion of the growth of silicon carbide epitaxial layers on silicon carbide substrates is set forth for example in U.S. Patents Nos. 4,912,063 to Davis et al. and 4,912,064 to Kong et al., the contents of both of which are incorporated entirely herein by reference.

The use of a cold wall reactor to carry out epitaxial growth, although satisfactory in many respects, raises other problems. In particular, because a semiconductor wafer rests on a susceptor, the wafer side in contact with the susceptor will become warmer than the remainder of the substrate. This causes a thermal gradient in the axial direction through the wafer. In turn, the difference in thermal expansion within the wafer caused by the axial gradient tends to cause the

peripheral edges (typically the circumference because most wafers are disc-shaped) to curl away from, and lose contact with, the susceptor. As the edges lose contact with the susceptor, their temperature becomes lower than the more central portions of the wafer, thus producing a radial temperature gradient in the substrate wafer in addition to the axial one.

These temperature gradients, and the resulting physical effects, have corresponding negative affects on the characteristics of the substrate and the epitaxial layers upon it. For example, if the edges are placed in extreme tension, they have been observed to crack and fail catastrophically. Even if catastrophic failure is avoided, the epitaxial layers tend to contain defects. At silicon carbide CVD growth temperatures (e.g. 1300°-1800°C), and using larger wafers (i.e. two inches or larger), wafer bending becomes a significant problem. For example, Figure 3 herein plots the values of wafer deflection (H) at various axial temperature gradients as a function of the wafer diameters.

Furthermore, because wafers have a finite thickness, the heat applied by the susceptor tends to generate another temperature gradient along the central axis of the wafer. Such axial gradients can both create and exacerbate the problems listed above.

Yet another temperature gradient typically exists between the rear surface of the substrate wafer and the front surface of the susceptor; i.e. a surface-to-surface gradient. It will thus be understood that both radiant and conductive heat transfer typically take place between susceptors and substrate wafers. Because many susceptors are formed of graphite coated with silicon carbide, the thermodynamic driving force created by the large temperature gradients between the susceptor and the silicon carbide wafers also causes the silicon carbide

coating to undesirably sublime from the susceptor to the wafer.

5        Additionally, because such sublimation tends to promote pin hole formation in the susceptor coating, it can permit contaminants from the graphite to escape and unintentionally dope the substrates or the epilayers. This in turn ultimately leads to non-uniform doping levels in the semiconductor material, and reduces the lifetime of the susceptor. The problems created by susceptors which undesirably emit dopants  
10        is set forth for example in the background portion of U.S. Patent No. 5,119,540 to Kong et al.

15        Nevertheless, a need still exists for susceptors that can operate at the high temperatures required for silicon carbide processing while minimizing or eliminating these radial, axial and surface to surface temperature gradients, and the associated physical changes and problems.

#### Object and Summary of the Invention

20        Therefore, it is an object of the present invention to provide a susceptor for minimizing or eliminating radial, axial and surface-to-surface thermal gradients across a substrate wafer.

25        The invention meets this object with a susceptor that comprises a first portion that includes a surface for receiving a semiconductor substrate wafer thereon, and a second portion facing the substrate receiving surface and spaced from the substrate receiving surface with the spacing being sufficiently large to permit the flow of gases therebetween for epitaxial growth on a substrate. The spacing remains small enough, however, for the second susceptor  
30        portion to heat the exposed face of a substrate to substantially the same temperature as the first susceptor



portion heats the face of the substrate that is in direct contact with the substrate receiving surface.

In another aspect, the invention is a method for minimizing or eliminating thermal gradients in and around a substrate during epitaxial growth by heating a portion of a susceptor that faces, but avoids contact with, a semiconductor substrate, and that is spaced sufficiently far from the substrate to permit the flow of gases between the substrate and the susceptor portion to encourage epitaxial growth on the substrate facing the susceptor portion wherein the susceptor is thermally responsive to the irradiating radiation.

The foregoing and other objects, advantages and features of the invention, and the manner in which the same are accomplished, will be more readily apparent upon consideration of the following detailed description of the invention taken in conjunction with the accompanying drawings, which illustrate preferred and exemplary embodiments, and wherein:

#### Brief Description of the Drawings

Figure 1 is a cross-sectional view of a platform type chemical vapor deposition (CVD) system;

Figure 2 is a cross-sectional view of a barrel-type CVD system;

Figure 3 is a graph illustrating the relationship between wafer deflection and wafer diameter at various temperature gradients;

Figure 4 is a schematic view of a barrel-type susceptor;

Figure 5 is a schematic view of wafer deflection and temperature gradients;

Figure 6 is a cross-sectional view of one embodiment of a susceptor according to the present invention;

Figure 7 is a partial cross-sectional view of a second embodiment of the susceptor of the present invention;

Figure 8 is a cross-sectional view of a pancake-type susceptor;

Figure 9 is a top plan view of a pancake-type susceptor; and

5        Figure 10 is a cross-sectional view of a pancake-type susceptor according to the present invention.

#### Detailed Description of the Preferred Embodiments

10        The present invention is a susceptor for minimizing or eliminating thermal gradients, including radial, axial, and surface-to-surface gradients, that affect a substrate wafer during epitaxial growth. Substrates according to the present invention are particularly useful for chemical vapor deposition systems as illustrated in Figures 1 and 2. Figure 1 shows a platform or pancake type CVD system broadly  
15        designated at 20. The system comprises a reactor vessel 21 formed of a material, typically a quartz tube or bell jar, that is substantially transparent to the appropriate frequencies of electromagnetic radiation. A gas supply system is in fluid communication with the reaction vessel 21 and in  
20        Figure 1 is illustrated as the gas injector 22.

25        The system includes a source of electromagnetic radiation that in Figure 1 is illustrated as the induction coils 25. The operation of such generators and induction coils is generally well known to those of ordinary skill in the art, and will not be discussed further herein in detail. As is  
30        also understood in this art, alternative heating techniques can include electric resistance heating, radiant lamp heating, and similar techniques.

30        The chemical vapor deposition system shown in Figure 1 also includes the platform type susceptor 26 with semiconductor substrates, typically disc-shaped wafers 27.

thereon. Figure 1 also illustrates the pumping port 30 for evacuating the system as desired.

Figure 2 illustrates a system that is very similar in terms of its basic operation, but that is a barrel-type susceptor, rather than a pancake-type. In Figure 2, the CVD system is broadly designated at 32 and shows a reaction vessel 33 which is surrounded by a water jacket 34 which circulates water against the walls of the reaction vessel 33. The CVD system 32 also includes a gas inlet 35 and a gas exhaust 36, a water inlet 37 and the water outlet 40, and a lifting and rotation assembly 41 for the susceptor.

The susceptor itself is broadly designated at 42 and is in the general shape of a cylinder, although with a shallow slope that gives it somewhat frustoconical shape. The cylinder is formed of a plurality of adjacent straight sidewall sections 43 that define the cylinder. A plurality of wafer pockets 44 are positioned on the sidewalls 43 and hold the semiconductor substrates thereon. The slight incline of the susceptor walls help keep the wafers in the pockets 44, and improve the uniformity of the resulting epilayers by encouraging more favorable gas flow. Figure 2 also illustrates the power supply 45 for the induction coil broadly designated at 46.

Figure 3 is a graph that helps illustrate the problem addressed by the present invention. In Figure 3, the deflection of a wafer expressed in thousandths of an inch is plotted against the wafer diameter in inches for three different temperature gradients ("Delta T"). As noted in Figure 3, the susceptor surface temperature is 1530°C and the wafer thickness is 12 mils (0.012 inch). As Figure 3 illustrates, wafer deflection represents a minimal problem when the diameter of the substrate wafer is about an inch or less. For larger wafers, particularly those of two, three or

even four inches, the deflection becomes more severe, even at relatively low temperature gradients.

Figure 4 illustrates a barrel type susceptor similar to that used in the illustration of Figure 2. Using the same numbering system as Figure 2, the susceptor is broadly designated at 42, is made of a plurality of straight sidewalls 43 that together define the generally cylindrical shape. The sidewalls 43 include a plurality of wafer pockets 44 for holding the substrate wafer.

Figure 5 is a schematic illustration of the effects of the temperature gradients plotted in Figure 3, and includes the designation of the axial temperature gradient ( $\Delta T_1$ ) and of the radial gradient ( $\Delta T_2$ ).

Figure 6 illustrates a susceptor according to the present invention that is most appropriately used in the barrel type systems illustrated in Figure 2. In the embodiment illustrated in Figure 6, the susceptor is broadly designated at 50 and is a cylinder formed of a plurality of adjacent straight sidewall sections 51. Figure 6 illustrates two of the sidewalls in cross-section and one in side elevation. The straight sidewall sections 51, of which there are most typically four, six, or eight, are formed of a material that is thermally responsive to selected frequencies of electromagnetic radiation. As noted above, the most common electromagnetic radiation is in the radio frequency range, so the susceptor material is generally selected to be thermally responsive to such RF frequencies. In preferred embodiments, the susceptor 50 is formed of graphite coated with silicon carbide.

In a presently preferred embodiment, the electromagnetic radiation is applied in the 8-10 kilocycle range using a solid state power supply that takes advantage of the inherent efficiencies of solid state technology. Those familiar with inductive CVD processes will also recognize that thicker

susceptor walls require lower frequencies to achieve the most efficient penetration.

In the embodiment illustrated in Figure 6, the susceptor 50 includes a plurality of wafer pockets 52 on the inner circumference of the cylinder. Thus, when the susceptor 50 is heated, the facing walls radiantly heat the front of the wafers while the susceptor heats the rear. As Figure 6 illustrates, in this embodiment, the sidewalls 51 preferably define an inverted truncated cone with a relatively shallow slope as compared to a true cylinder. As noted earlier, the shallow slope in the sidewalls 51 makes it somewhat easier to retain the wafers in the pockets 52 during chemical vapor deposition, and also helps provide a proper flow pattern for the CVD gases.

Figure 7 illustrates a next embodiment of the invention in which the susceptor comprises a first cylinder (or "barrel") broadly designated at 54. The cylinder is defined by a plurality of adjacent straight sidewall sections 55, and is formed of a material that is thermally responsive to selected frequencies of electromagnetic radiation. The cylinder 54 includes a plurality of wafer pockets 56 on the outer surface of the sidewall sections 55.

A second cylinder broadly designated at 57 surrounds the first cylinder 54 and defines an annular space A between the first and second cylinders. The second cylinder 57 is likewise made of a material that is thermally responsive to the selected frequencies of electromagnetic radiation, and the annular space between the first and second cylinders (54, 57) is sufficiently large to permit the flow of gases therebetween for epitaxial growth on substrates in the wafer pockets 56, while small enough for the second cylinder 57 to heat the exposed face of substrates to substantially the same temperature as the first cylinder 54 heats the faces of substrates that are in direct contact with the first cylinder.

The first and second cylinders 54, 57 can be formed of either the same or different materials. If used in a barrel type susceptor system as illustrated in Figure 2, the second cylinder 57 tends to heat the first cylinder 54 to encourage the cylinders to reach substantially the same temperatures. As in other embodiments, each of the cylinders is most preferably formed of graphite coated with silicon carbide.

It will be understood that the use of a silicon carbide coating on such susceptors is a function of the ceramic properties of polycrystalline silicon carbide and is otherwise not related to its semiconductor properties. Thus, susceptors made of stainless steel, graphite, graphite coated with silicon carbide, or silicon carbide, are typically used in the semiconductor industry for CVD processes.

Figures 8, 9 and 10 illustrate another susceptor according to the present invention. Figures 8 and 9 illustrate, in cross-section and top plan view respectively, a pancake or plate-shaped susceptor broadly designated at 60. The susceptor 60 has a top surface 61 for receiving semiconductor substrate wafers thereon. In this embodiment, the invention further comprises a horizontally disposed second susceptor portion 63 parallel to and above the wafer receiving surface 61 of the first susceptor portion 60. Both of the susceptor portions 60 and 63 are formed of materials that are thermally responsive to selected frequencies of electromagnetic radiation, and as in the previous embodiments, are preferably formed of the same material to be responsive to the same frequencies of electromagnetic radiation. Most preferably, both susceptor portions 60 and 63 are formed of graphite coated with silicon carbide. As in the previous embodiments, the spacing designated B (Figure 10) between the two portions 60, 63 is sufficiently large to permit the flow of gases therebetween for epitaxial growth on a substrate on the surface 61, while small enough for the second susceptor

portion 63 to heat the exposed face of a substrate to substantially the same temperature as the first susceptor portion 60 heats the face of substrate that is in direct contact with the substrate receiving surface 61. As  
5 illustrated in Figures 8, 9 and 10, the top surface 61 of the first horizontal susceptor portion 60 preferably includes a plurality of wafer pockets 64.

In each of these embodiments, it will be understood that the two susceptor portions can be connected to one another, or  
10 separate portions of a single susceptor, or independent pieces as may be desired or necessary under various circumstances. Additionally, the optimum spacing between the substrate portions can be determined by computer modeling or actual practice, and without requiring undue experimentation.

In another aspect, the invention comprises a method for minimizing or eliminating thermal gradients in a substrate during epitaxial growth. In this aspect, the invention  
15 comprises irradiating a susceptor, or a susceptor portion, that faces, but avoids contact with, a semiconductor substrate wafer, and that is spaced sufficiently far from the wafer to permit the flow of gases between the substrate and the facing  
20 susceptor to thereby encourage epitaxial growth on the substrate facing the susceptor portion. As in the structural embodiments, the susceptor is thermally responsive to the  
25 irradiating radiation.

As further set forth with respect to the structural aspects of the invention, the invention also preferably  
comprises concurrently irradiating a separate susceptor portion upon which the wafer rests so that the exposed face of  
30 the substrate is heated to substantially the same temperature as is the face of the substrate that is in direct contact with the other susceptor portion.

The method further comprises the steps of directing source gases that flow between the heated susceptor portions.

If the epitaxial layers are to be formed of silicon carbide, the method preferably comprises directing silicon and carbon containing source gases such as silane, ethylene, and propane.

Where other materials, such as Group III nitrides, are to form the epitaxial layers on the silicon carbide, the step of directing source gases can include directing gases such as trimethyl aluminum, trimethyl gallium, trimethyl indium, and ammonia.

In preferred embodiments, the method also comprises the step of preparing the substrate surface for growth. As set forth in more detail in the references incorporated above, such preparation can comprise steps such as oxidizing the surface followed by a chemical etching step to remove the oxidized portion leaving a prepared surface behind, or alternatively, dry etching the silicon carbide surface to prepare it for further growth. As in most epitaxial growth technique, surface preparation further typically comprises lapping and polishing the substrate surface prior to the oxidation or etching steps.

In the drawings and specifications, there have been disclosed typically preferred embodiments of the invention and, although specific terms have been employed, they have been used in a generic sense and in descriptive sense only, and not for purposes of limitation, the scope of the invention being set forth in the following claims:



THAT WHICH IS CLAIMED:

1. A susceptor for minimizing or eliminating thermal gradients that affect a substrate wafer during epitaxial growth, said susceptor comprising:

5 a first susceptor portion including a surface for receiving a semiconductor substrate wafer thereon; and

10 a second susceptor portion facing said substrate-receiving surface and spaced from said substrate-receiving surface, said spacing being sufficiently large to permit the flow of gases therebetween for epitaxial growth on a substrate on said surface, while small enough for said second susceptor portion to heat the exposed face of a substrate to substantially the same temperature as said first susceptor portion heats the face of a substrate that is in direct contact with said substrate-receiving surface.

2. A barrel-type susceptor according to Claim 1.

3. A pancake-type susceptor according to Claim 1.

4. A susceptor according to Claim 1 wherein said first susceptor portion is formed of a material that is thermally responsive to electromagnetic radiation.

5. A susceptor according to Claim 1 wherein said second susceptor portion is formed of a material that is thermally responsive to electromagnetic radiation.

6. A susceptor according to Claim 1 wherein said first and second portions are formed of the same material.

7. A susceptor according to Claim 1 wherein said first and second portions are formed of different materials.

8. A susceptor according to Claim 1 wherein said first susceptor portion is formed of graphite coated with silicon carbide.

9. A susceptor according to Claim 1 wherein said second susceptor portion is formed of graphite coated with silicon carbide.

10. A susceptor according to Claim 1 wherein said substrate receiving surface further comprises a plurality of wafer pockets.

11. A method for minimizing or eliminating thermal gradients that affect a substrate during epitaxial growth, the method comprising:

heating a portion of a susceptor that faces, but avoids contact with, a semiconductor substrate and that is spaced sufficiently far from the substrate to permit the flow of gases between the substrate and the susceptor portion to encourage epitaxial growth on the substrate facing the susceptor portion.

12. A method according to Claim 11 and further comprising concurrently heating a second susceptor portion upon which the wafer rests so that the exposed face of the substrate is heated to substantially the same temperature as is the face of the substrate that is in direct contact with the second susceptor portion.

13. A method according to Claim 11 wherein the heating step comprises irradiating a susceptor that is thermally responsive to certain frequencies of the electromagnetic radiation with electromagnetic radiation within the range of those certain frequencies.

14. A method according to Claim 12 and further comprising the step of directing source gases to flow between the heated susceptor portions.

15. A method according to Claim 12 wherein the source gases are selected from the group consisting of silane, ethylene, propane and mixtures thereof.

16. A method according to Claim 12 wherein the source gases comprise trimethyl gallium and ammonia.

17. A method according to Claim 14 and further comprising the step of preparing the substrate surface for growth.

18. A method according to Claim 17 wherein the substrate comprises silicon carbide, and the surface preparation comprises an oxidation step followed by a chemical etching step to remove the oxidized portion.

19. A method according to Claim 17 wherein the substrate comprises silicon carbide, and the surface preparation comprises dry etching the silicon carbide surface.

20. A method according to Claim 17 wherein the surface preparation comprises lapping and polishing the substrate surface.

21. A chemical vapor deposition system comprising:  
a reactor vessel formed of a material substantially transparent to electromagnetic radiation;  
a gas supply system in fluid communication with said  
5 reactor vessel;

a source of electromagnetic radiation external to said reaction vessel; and

a susceptor within said reaction vessel, and formed of a material that is thermally responsive to electromagnetic radiation, said susceptor comprising,

a first susceptor portion including a surface for receiving a semiconductor substrate wafer thereon; and

a second susceptor portion facing said substrate-receiving surface and spaced from said substrate-receiving surface, said spacing being sufficiently large to permit the flow of gases therebetween for epitaxial growth on a substrate on said surface, while small enough for said second susceptor portion to heat the exposed face of a substrate to substantially the same temperature as said first susceptor portion heats the face of a substrate that is in direct contact with said substrate-receiving surface.

22. A chemical vapor deposition system according to Claim 21 wherein said reaction vessel is made of quartz.

23. A chemical vapor deposition system according to Claim 21 wherein said reaction vessel is made of stainless steel.

24. A chemical vapor deposition system according to Claim 21 wherein said source of electromagnetic radiation comprises an induction coil surrounding said reaction vessel.

25. A chemical vapor deposition system according to Claim 21 wherein said first and second portions are formed of the same material.

26. A chemical vapor deposition system according to Claim 21 wherein said first and second portions are formed of different materials.

27. A chemical vapor deposition system according to Claim 21 wherein said first susceptor portion is formed of graphite coated with silicon carbide.

28. A chemical vapor deposition system according to Claim 21 wherein said second susceptor portion is formed of graphite coated with silicon carbide.

29. A chemical vapor deposition system according to Claim 21 wherein said substrate receiving surface on said first substrate portion comprises a plurality of wafer pockets.

30. A chemical vapor deposition system according to Claim 21 wherein said susceptor comprises:

a cylinder formed of a plurality of adjacent straight sidewall sections that define the cylinder; and

a plurality of wafer pockets on the inner circumference of said cylinder.

31. A chemical vapor deposition system according to Claim 21 wherein said first susceptor portion comprises a first cylinder formed of a plurality of adjacent straight sidewall sections that define the cylinder; and

a plurality of wafer pockets on the outer surface of said sidewall sections; and

said second susceptor portion comprises a second cylinder surrounding said first cylinder and defining an annular space between said first and second cylinders, with the annular space between said first and second cylinders being

15 sufficiently large to permit the flow of gases therebetween  
for epitaxial growth on substrates in said wafer pockets,  
while small enough for said second cylinder to heat the  
exposed face of substrates to substantially the same  
temperature as said first cylinder heats the faces of  
substrates that are in direct contact with said first  
cylinder.

32. A chemical vapor deposition system according to  
Claim 21 wherein said first susceptor portion is a horizontal  
platform having a top surface for receiving semiconductor  
substrate wafers thereon; and

5 said second susceptor portion is parallel to and spaced  
above said wafer-receiving surface of said first susceptor  
portion, said spacing being sufficiently large to permit the  
flow of gases therebetween for epitaxial growth on a substrate  
on said surface, while small enough for said second susceptor  
10 portion to heat the exposed face of a substrate to  
substantially the same temperature as said first susceptor  
portion heats the face of a substrate that is in direct  
contact with said substrate-receiving surface.

33. A susceptor for minimizing or eliminating thermal  
gradients across a substrate wafer, said susceptor comprising:

5 a cylinder formed of a plurality of adjacent straight  
sidewall sections that define the cylinder, said cylinder  
being formed of a material that is thermally responsive to  
selected frequencies of electromagnetic radiation; and

a plurality of wafer pockets on the inner circumference  
of said cylinder.

34. A susceptor according to Claim 33 wherein said  
sidewalls define an inverted truncated cone.

35. A susceptor according to Claim 33 wherein said susceptor material in said cylinder is thermally responsive to radio frequencies.

36. A susceptor according to Claim 33 wherein said cylinder is formed of graphite coated with silicon carbide.

37. A susceptor for minimizing or eliminating thermal gradients across a substrate wafer, said susceptor comprising:

a first cylinder formed of a plurality of adjacent straight sidewall sections that define the cylinder, said cylinder being formed of a material that is thermally responsive to selected frequencies of electromagnetic radiation;

a plurality of wafer pockets on the outer surface of said sidewall sections; and

a second cylinder surrounding said first cylinder and defining an annular space between said first and second cylinders, said second cylinder being made of a material that is thermally responsive to selected frequencies of electromagnetic radiation, with the annular space between said first and second cylinders being sufficiently large to permit the flow of gases therebetween for epitaxial growth on substrates in said wafer pockets, while small enough for said second cylinder to heat the exposed face of substrates to substantially the same temperature as said first cylinder heats the faces of substrates that are in direct contact with said first cylinder.

38. A susceptor according to Claim 37 wherein said first and second cylinders are formed of the same material and are responsive to the same frequencies of electromagnetic radiation.

39. A susceptor according to Claim 37 wherein said first and second cylinders are thermally responsive to radio frequency electromagnetic radiation.

40. A susceptor according to Claim 37 wherein said first cylinder is formed of graphite coated with silicon carbide.

41. A susceptor according to Claim 37 wherein said second cylinder is formed of graphite coated with silicon carbide.

42. A susceptor for minimizing or eliminating thermal gradients across a substrate wafer, said susceptor comprising:

a first susceptor portion formed of a material that is thermally responsive to selected frequencies of electromagnetic radiation, and having a top surface for receiving semiconductor substrate wafers thereon; and

a second susceptor portion parallel to and spaced apart from said wafer-receiving surface of said first susceptor portion and formed of a material that is thermally responsive to selected frequencies of electromagnetic radiation, said spacing being sufficiently large to permit the flow of gases therebetween for epitaxial growth on a substrate on said surface, while small enough for said second susceptor portion to heat the exposed face of a substrate to substantially the same temperature as said first susceptor portion heats the face of a substrate that is in direct contact with said substrate-receiving surface.

43. A susceptor according to Claim 42 wherein said first and second susceptor portions are horizontally oriented.



44. A susceptor according to Claim 42 wherein said first and second susceptor portions are formed of the same material and are responsive to the same frequencies of electromagnetic radiation.

45. A susceptor according to Claim 42 wherein said first and second susceptor portions are thermally responsive to radio frequency electromagnetic radiation.

46. A susceptor according to Claim 42 wherein said first susceptor portion is formed of graphite coated with silicon carbide.

47. A susceptor according to Claim 42 wherein said second susceptor portion is formed of graphite coated with silicon carbide.

48. A susceptor according to Claim 42 wherein said top surface of said first susceptor portion includes a plurality of wafer pockets.

## SUSCEPTOR DESIGNS FOR SILICON CARBIDE THIN FILMS

### Abstract of the Disclosure

A susceptor is disclosed for minimizing or eliminating thermal gradients that affect a substrate wafer during epitaxial growth. The susceptor comprises a first susceptor portion including a surface for receiving a semiconductor substrate wafer thereon, and a second susceptor portion facing the substrate-receiving surface and spaced from the substrate-receiving surface. The spacing is sufficiently large to permit the flow of gases therebetween for epitaxial growth on a substrate on the surface, while small enough for the second susceptor portion to heat the exposed face of a substrate to substantially the same temperature as the first susceptor portion heats the face of a substrate that is in direct contact with the substrate-receiving surface.

244138

OFFICE OF THE SECRETARY




Fig. 1.

WATER OUTLET 40

GAS INLET 35

32

43 44

42

33

34

46

45

COIL POWER SUPPLY

WATER INLET 37

GAS EXHAUST 36

SUSCEPTOR LIFT/ROTATION ASSEMBLY 41

WATER INLET 36

GAS EXHAUST 36

—fig. 2.




FIG. 3.




FIG. 4.




FIG. 5.





FIG. 6.

[illegible]

—fig. 7.




FIG. 8.




FIG. 9.




FIG. 10.



Please type a plus sign (+) inside this box → ☐

PTO/SB/01 (3-97)  
Approved for use through 9/30/98. OMB 0651-0032  
Patent and Trademark Office; U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it contains a valid OMB control number.

## DECLARATION FOR UTILITY OR DESIGN PATENT APPLICATION

☐ Declaration  
Submitted  
with Initial  
Filing

OR

☒ Declaration  
Submitted after  
Initial Filing

Attorney Docket Number	5000.89
First Named Inventor	Kong
<b>COMPLETE IF KNOWN</b>	
Application Number	08/823,365
Filing Date	March 24, 1997
Group Art Unit	1109
Examiner Name	

As a below named inventor, I hereby declare that:

My residence, post office address, and citizenship are as stated below next to my name.

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled:

**SUSCEPTOR DESIGNS FOR SILICON CARBIDE  
THIN FILMS**

(Title of the Invention)

the specification of which

☐ is attached hereto  
OR

☒ was filed on (MM/DD/YYYY) **03/24/1997** as United States Application Number or PCT International

Application Number **08/823,365** and was amended on (MM/DD/YYYY) (if applicable).

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment specifically referred to above.

I acknowledge the duty to disclose information which is material to patentability as defined in Title 37 Code of Federal Regulations, § 1.56.

I hereby claim foreign priority benefits under Title 35, United States Code §119 (a)-(d) or § 365(b) of any foreign application(s) for patent or inventor's certificate, or §365 (a) of any PCT international application which designated at least one country other than the United States of America, listed below and have also identified below, by checking the box, any foreign application for patent or inventor's certificate, or of any PCT international application having a filing date before that of the application on which priority is claimed.

Prior Foreign Application Number(s)	Country	Foreign Filing Date (MM/DD/YYYY)	Priority Not Claimed	Certified Copy Attached?	
				YES	NO
			<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
			<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
			<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
			<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
			<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
			<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>

☐ Additional foreign application numbers are listed on a supplemental priority data sheet PTO/SB/02B attached hereto:

I hereby claim the benefit under Title 35, United States Code § 119(e) of any United States provisional application(s) listed below.

Application Number(s)	Filing Date (MM/DD/YYYY)	<input type="checkbox"/> Additional provisional application numbers are listed on a supplemental priority data sheet PTO/SB/02B attached hereto.

[Page 1 of 2]

Burden Hour Statement: This form is estimated to take 0.4 hours to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, Patent and Trademark Office, Washington, DC 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Assistant Commissioner for Patents, Washington, DC 20231.

Please type a plus sign (+) inside this box → +

PTO/SB/01 (3-97)

Approved for use through 9/30/98. OMB 0651-0032  
Patent and Trademark Office; U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it contains a valid OMB control number.

## DECLARATION — Utility or Design Patent Application

I hereby claim the benefit under Title 35, United States Code §120 of any United States application(s), or §365(c) of any PCT international application designating the United States of America, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT International application in the manner provided by the first paragraph of Title 35, United States Code §112, I acknowledge the duty to disclose information which is material to patentability as defined in Title 37, Code of Federal Regulations §1.56 which became available between the filing date of the prior application and the national or PCT international filing date of this application.

U.S. Parent Application Number	PCT Parent Number	Parent Filing Date (MM/DD/YYYY)	Parent Patent Number (if applicable)

☐ Additional U.S. or PCT international application numbers are listed on a supplemental priority data sheet PTO/SB/02B attached hereto.

As a named inventor, I hereby appoint the following registered practitioner(s) to prosecute this application and to transact all business in the Patent and Trademark Office connected therewith:

☐ Customer Number

OR

☒ Registered practitioner(s) name/registration number listed below

Place Customer  
Number Bar Code  
Label here

Name	Registration Number	Name	Registration Number
PHILIP SUMMA	31,573		

☐ Additional registered practitioner(s) named on supplemental Registered Practitioner Information sheet PTO/SB/02C attached hereto.

Direct all correspondence to: ☐ Customer Number or Bar Code Label ☒ Correspondence address below

Name	PHILIP SUMMA						
Address	5925 Carnegie Blvd., Suite 500						
Address							
City	Charlotte	State	NC	ZIP	28209		
Country	US	Telephone	704/571-3848		Fax	704/571-3847	

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Name of Sole or First Inventor:

☐ A petition has been filed for this unsigned inventor

Given Name (first and middle [if any])				Family Name or Surname			
Hua-Shuang				Kong			
Inventor's Signature	<i>Huashuang Kong</i>					Date	12/2/97
Residence: City	Raleigh	State	NC	Country	US	Citizenship	CN
Post Office Address	10840 Bexhill Drive						
Post Office Address							
City	Raleigh	State	NC	ZIP	27606	Country	US

☒ Additional inventors are being named on the 1 supplemental Additional Inventor(s) sheet(s) PTO/SB/02A attached hereto



Please type a plus sign (+) inside this box → ☐

PTO/SB/02A (3-97)  
Approved for use through 9/30/98. OMB 0651-0032  
Patent and Trademark Office; U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it contains a valid OMB control number.

## DECLARATION

ADDITIONAL INVENTOR(S)  
Supplemental Sheet  
Page 1 of 1

Name of Additional Joint Inventor, if any:				<input type="checkbox"/> A petition has been filed for this unsigned inventor			
Given Name (first and middle (if any))				Family Name or Surname			
Calvin				Carter, Jr.			
Inventor's Signature				Date	12/2/97		
Residence: City	Cary	State	NC	Country	US	Citizenship	US
Post Office Address	114 N. Drawbridge Lane						
Post Office Address							
City	Cary	State	NC	ZIP	27513	Country	US
Name of Additional Joint Inventor, if any:				<input type="checkbox"/> A petition has been filed for this unsigned inventor			
Given Name (first and middle (if any))				Family Name or Surname			
Joseph				Sumakeris			
Inventor's Signature				Date	12/2/97		
Residence: City	Apex	State	NC	Country	US	Citizenship	US
Post Office Address	1114 Chaney Circle						
Post Office Address							
City	Apex	State	NC	ZIP	27502	Country	US
Name of Additional Joint Inventor, if any:				<input type="checkbox"/> A petition has been filed for this unsigned inventor			
Given Name (first and middle (if any))				Family Name or Surname			
Inventor's Signature				Date			
Residence: City		State		Country		Citizenship	
Post Office Address							
Post Office Address							
City		State		ZIP		Country	

Burden Hour Statement: This form is estimated to take 0.4 hours to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, Patent and Trademark Office, Washington, DC 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Assistant Commissioner for Patents, Washington, DC 20231.